

## Description

Acrylic Low Sheen (9% sheen) is a versatile and durable low reflective paint with the hiding qualities of a matt finish, whilst also being resistant to marking and burnishing. Marks and scuffs can be easily cleaned by wiping with a damp cloth. The high scrub resistance and inherent resistance to mould growth make this product an ideal paint for all internal walls and surfaces, including those situated in wet areas and high use areas where a matt effect is desired.

It can be used as a primer for bare wood and a mist coat for sealing new gypsum plaster and plasterboard jointing compound prior to applying top coats. This means one product is all you need and you save on labour and product.

## Typical Uses

- Interior gypsum plaster, plasterboard and timber surfaces
- High use areas including offices, commercial areas including back-of-house and corridors, public building and residential spaces
- High humidity areas including bathrooms and kitchens
- Interior ceilings and walls in moderate traffic areas

## Physical Properties

Sheen level*	7%
Coverage	Up to 20 square metres per litre per coat (varies with substrate and texture)
Recommended dry film thickness	30 microns per coat
Recommended number of coats	Two
Touch dry and recoat time	Between 20 minutes and 1 hour (dependant on atmospheric conditions)
Scrub resistance	Class 1
Volume solids	32%
Colour availability	Any published colour range
Pack sizes	2.5, 5 and 10 litres
Odour	Virtually nil

\*Final sheen level is given based upon two full coats being applied

## Environment

2010 maximum permitted limit grams per litre	30g/l
VOC category for this product	a
Actual VOC content grams per litre	14 g/l
Classification	Minimal

## Health & Safety

Our products are designed to cause no harm. Detailed safety information is available on our website or on request.

## Surface Preparation

Ensure that surfaces are free from dirt, dust, grease, mould and any other contaminants that may affect adhesion. Clean off any surface mould with anti-fungicidal cleaner and rinse off. Contaminated areas should be washed down thoroughly with sugar soap and rinsed off. Once cleaned, lightly sand surface to form a key and then clean with

a lint free cloth. Imperfections, such as gloss and loose, flaking paint should be sanded to remove as required, and all dry painted edges feathered off to a smooth finish.

Holes, impressions and cracks must be filled with proprietary surface fillers as required. Powdered fillers such as Tetriol, Polyfiller or similar are not recommended. For best results use Easifill, Red Devil, Onetime or two pack fillers for wood. Spot prime all surface fillers with Paintfinity Acrylic All Purpose Primer before the application of top coats.

### Previously painted gypsum, fibrous plaster and paper faced plasterboard and jointing

Clean to remove any surface contaminants and sand to feather any raw edges of existing paint / coating. Fine fill using a proprietary filler as required and apply mist coat of Paintfinity Low Sheen to any filled surfaces to seal, thinned in accordance with thinning guidelines, before applying top coats.

### New gypsum, fibrous plaster and paper faced plasterboard and jointing

Ensure that plaster and jointing fillers are dry, sanded as necessary and free from dust before beginning the application of any paint. Apply one mist coat of Paintfinity Low Sheen as a sealer, thinned in accordance with thinning guidelines, before applying top coats.

### New timber surfaces

For soft wood, knots should be treated with a proprietary knotting solution to prevent bleed through. Ensure that the wood is completely dry. Paintfinity Acrylic All Purpose Primer is necessary for exterior timber surfaces prior to applying the top coat. For interior timber Paintfinity Acrylic Matt or Acrylic Low Sheen can be applied as a primer instead if preferred.

### Timber surfaces previously painted with acrylic paint and alkyd paint

No undercoat is required when correct preparation has been completed. Clean and sand lightly to provide a key to aid adhesion.

### Plastics

Clean and lightly sand to provide a key followed by an application of Paintfinity Acrylic All Purpose Primer before applying top coats.

## Application

This product can be applied in temperatures between 5°C and 30°C. Take care to avoid contact with the painted surface before the product has been able to dry. Always follow the touch dry and recoat times stated above.

### Brushing

Use only high quality synthetic brushes suitably sized for the job in hand. Ensure that brushes are sufficiently dry after washing out before use.

Apply paint generously with even brush strokes maintaining a wet edge as you progress leaving the paint to find its own level. Do not overwork and take care not to brush over paint that has already started to dry.

In high temperatures, paint pail open times can be extended by dilution with water at the ratio of no more than 1% by volume.

**Roller**

Use only short napped synthetic rollers for the best result on smooth surfaces. The nap length can be increased for textured surfaces as required. Take care to maintain a wet edge and to avoid lapping marks and flashing. Never over roller paint that has started to dry.

In high temperatures the open time can be extended by dilution with water at the ratio of no more than 5% by volume.

**Spray application**

For airless spray application, dilute paint by 25%. Use tip sizes and pressure based upon the job in hand. In all instances, seek technical guidance from the manufacturers of the spray equipment.

**Clean Up & Disposal**

Remove excess paint from all equipment. The cleaning of brushes and rollers should be carried out immediately using clean water. Cleaning is most effective if the water is slightly warm.

**Storage & Shelf Life**

Storage of paint should be in a cool dry and frost-free environment. Products that are unopened can be stored indefinitely. Products that have been opened and part used can be stored for 2 years, providing the lid is securely and correctly fitted, and providing no contamination has been allowed to enter the paint. All products will need to be stirred thoroughly prior to use following extended periods of time in storage.

**Life Cycle Maintenance****Cleaning**

For light soiling and marking, wipe the surface using a clean semi-dry cloth and diluted light detergent such as washing up liquid.

**Touching in**

Whilst this is generally not recommended for perfect results, both marks that cannot otherwise be cleaned, and small repairs using fillers, can be satisfactorily touched in, provided that fillers are sealed with a primer or mist coat first. For best results, the method of original paint application should be used to carry out any touching in.

**Disclaimer** – The information in this product information sheet is correct to the best of our knowledge and experience. Paintfinity Ltd. reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.